



NAV PAD PIGMENTS PVT.LTD



REACH Status : Pre Registered

Date : 01.10.2016

Revision : 01


Product Description

CI Generic Name	PIGMENT VIOLET 23	NPPL Product Code	PL-9045
CI No.	51 319	CAS No.	6358-30-1
EINECS No.	228-767-9	Chemical Type	Dioxazine
Molecular Formula	C34H22Cl2N4O2	Molecular Weight	588
Chemical Name:Diindolo [3, 3', 2' M] triphenodioxazine, 8, 18 – dichloro – 5, 15 – diethyl – 5, 15 - dihydro			

Physical Properties

Sieve Residue (PPM) Max.	1000
Oil Absorption(gms)	-
Bulk Density(gm/ml)	-
Salt Content (%) Max.	1
Moisture Content (%) Max.	1
PH Value	5-7

Mass Tone : 5%



Tint Tone : 1:10 Ratio



Fastness properties

Heat °C	Mass Tone	280°C / 5 Min.
Heat °C	Tint Tone	280°C / 5 Min.
Light	Mass Tone	7-8
Light	Tint Tone	7-8
Weather	Mass Tone	4-5
Weather	Tint Tone	5
Migration		5

Specification

Coloristic properties-	Tint	Strength : ± 5 %
Coloristic properties-	Tint	DA,DB,DE,DC,DH,DL: ± 1
Light fastness :	Scale 1- 8	1~Poor & 8 ~ Excellent
Weather fastness :	Scale 1- 5	1~Poor & 5 ~ Excellent
Overspray :	Scale 1- 5	1~Poor & 5 ~ Excellent
Solvent Fastness:	Scale 1- 5	1~Poor & 5 ~ Excellent
Heat Stability °C		DE</=3 at Maximum temp.

Application

PP / HDPE / LDPE	•
Engineering Polymers	•
PVC	•
Rubber / Fiber	•
•	Suitable
o	Limited Suitability

Note: The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

REGD. OFFICE & FACTORY: Plot No. 1196/1/A & B, Village Rajpur, Ghumasan Patia Road, Chhatral - Mehsana Highway, Rajpur - 382 715, Gujarat, India. Phone : +91-2764-278338 ; +91-98250 31388

Website : www.navpadpigments.com Email: exports@navpadpigments.com